

No. S133025-2025



221520010916

检验报告

TEST REPORT

样 品 名 称：钢渣矿渣硅酸盐水泥

型 号 规 格：P·SS 42.5

送 检 单 位：日照明珠新型建材有限公司

检 验 类 别：型式检验

山东省乡镇企业建材质量监督检验中心

Shandong Township Enterprise Building Materials Quality Supervision and Inspection Center

山东省乡镇企业建材质量监督检验中心

Shandong Township Enterprise Building Materials Quality Supervision and Inspection Center

检 验 报 告

Test Report

共 2 页第 1 页

样品名称 Sample	钢渣矿渣硅酸盐水泥	检验类别 Test Kind	型式检验
送检单位 Client	日照明珠新型建材有限公司	型号规格 Model, Type	P·SS 42.5
生产单位 Manufacturer	日照明珠新型建材有限公司	样品等级 Grade	/
送检单位地址 Address of Client	日照市岚山区虎山镇于家官庄村	商 标 Brand	/
抽样地点 Sampling Location	/	送样人员 Client Representative	季相成 (邮寄)
抽样基数 Sample Batch	/	接样日期 Receipt Date	2025-10-21
样品数量 Sample Quantity	12kg	生产日期 Producing Date	2025-10-17
样品特性和状态 Sample Description	灰色粉状，塑料袋装	样品批号 Batch No.	DP011
检验日期 Test Date	2025-10-21~2025-11-20		
检验依据 Test Standard	GB/T 13590-2022		
检验要求 Test Item	型式检验		
检验结论 Test Conclusion	该样品按 GB/T 13590-2022 标准检验合格。		
备注 Note	1. 本报告含封面及封三，符号"/"表示该项无内容。		

批准:

审核:

编制: 王恒一



山东省乡镇企业建材质量监督检验中心

检 验 报 告 (续页)

共 2 页第 2 页

序号	检验项目		单位	技术要求	检验结果			单项判定
1	三氧化硫, %		/	≤4.0	2.6			合格
2	氯离子, %		/	≤0.06	0.05			合格
3	水泥中水溶性铬(Ⅵ)		mg/kg	≤10.0	4.4			合格
4	碱含量, %		/	/	0.50			/
5	密度		g/cm ³	/	2.82			/
6	细度	比表面积	m ² /kg	≥350	474			合格
7	凝结时间	初凝	min	≥45	233			合格
		终凝	min	≤600	311			合格
8	压蒸安定性, %		/	膨胀率≤0.50	0.03			合格
9	抗折强度	3d	MPa	≥4.0	$\bar{X} = 4.3$			合格
					4.3	4.4	4.3	
10	抗压强度	28d	MPa	≥6.5	$\bar{X} = 8.3$			合格
					8.1	8.4	8.3	
11		3d	MPa	≥17.0	$\bar{X} = 21.3$			合格
					21.0	21.2	21.1	
		28d	MPa	≥42.5	$\bar{X} = 45.6$			合格
					45.4	45.5	46.0	
12	放射性	内照射指数 I_{Ra}	/	$I_{Ra} \leq 1.0$	0.2			合格
		外照射指数 I_r		$I_r \leq 1.0$	0.3			
备 注			水溶性铬(Ⅵ)检出限为 0.3 mg/kg。					

*****以下空白*****

声 明

- 1、报告无“检验检测专用章”无效。
- 2、复制报告未重新加盖“检验检测专用章”无效。
- 3、报告无审核、批准人签字无效。
- 4、报告涂改无效。
- 5、除全文复制外，未经本机构批准不得部分复制报告。
- 6、送样检验，检验结果仅对来样负责。
- 7、送样检验样品及相关信息，均由委托单位提供，本机构不对其真实性及完整性负责。
- 8、如对本报告有异议，请于收到报告之日起15日内提出，逾期不予受理。



STATEMENT

- 1、The report without the specific seal for inspection report is invalid.
- 2、The copy of report without the specific seal for inspection report is invalid.
- 3、The report will be invalid without signature of person who was authorized to verify or approv it.
- 4、The report is not valid if altered.
- 5、This report can only be reproduced in whole and may not be partially reproduced without approval of this agency.
- 6、The report of sample-delivery test is valid only for the samples delivered by the clients.
- 7、Samples sent for inspection and related information are provided by the entrusting organization, and this agency is not responsible for its authenticity and integrity.
- 8、If there is any objection concerning the report, please submit it within 15 days upon reception of the report. The overdue request will not be accepted.

地址：山东省泰安市迎春路35号

邮编：271000

电话：(0538) 8222026

传真：(0538) 8226159